



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name

ACRYL PRIMER 1K by DECO COLOR® aerosol line

Article No

500 ml: 20 520; 20 530; 20 540. 20 550;
150 ml: 21 640; 21 650; 21 660

Seller/Manufacturer

Chemmot Ewa & Jerzy Kumorek spółka jawna; Piłsudskiego 59, 32-050 Skawina, Polska

Product's description

Fast drying 1K universal primer with good covering and filling properties. Protects against corrosion. Improves adhesion of topcoat. Compatible with all paint systems (alkyd, acrylic, nitro-combination) water and solvent based. Designed for priming surfaces made of metal, wood, aluminium, stone, concrete, plastic surfaces, except of some plastics and styrofoam. Wide range of application hobby and professional works: at home, garden, automotive and industry.

Main features

Protects against corrosion
Very good covering
Fills unevenness up effectively
Possibility of grinding when wet or dry
Petrol resistance
Primed surface could be covered by alkyd, acrylic, nitro-combination based paints
For indoor and outdoor use
CFC free

Physical and Chemical Properties

Capacity	150/500 ml
Base/resin	nitro-synthetic resin
Colour	grey, white, red oxide and black
Gloss	mat
Application temperature	15-25°C
Dust free	5-8 min
Touch free	15-20 min
Hardened	10-14 h
Cover capacity	500ml=2-2,5 m ² ; 150ml=0,8 m ² depending on colour and type of surface by one application
High temperature resistance	up to 100°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	good
Alcohol resistance	insufficient
Primer usage	n/a
Other coating applying	possible



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry. Primed surface should be grinded with fine-grained abrasive paper previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying). Drying time depends also on air humidity and product density. Painting should be made in well ventilated room. Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside. Perform the test spray. Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres. Wait few minutes between each layer when applying. When finished, clean the nozzle. Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 04 from 25/03/2014