



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name

BRAKE CALIPER by DECO COLOR® aerosol line

Article No

25 350; 25 351; 25 352; 25 353; 25 354; 25 355; 25 356; 25 357

Seller/Manufacturer

Chemmot Ewa & Jerzy Kumorek spółka jawna; Piłsudskiego 59, 32-050 Skawina, Polska

Product's description

High quality lacquer for brake calipers and drums, which gives them special sporty appearance. Very popular for optical tuning of cars and motorbikes. Brake caliper line has one of the best reputations among competitive products on the market.

Main features

Filling properties
Petrol resistance
Resistant to abrasion and weather conditions
Heat resistance up to 150°C
Protects against corrosion
High gloss
For indoor and outdoor use
CFC free

Physical and Chemical Properties

Capacity	400 ml
Base/resin	alkyd
Colour	yellow, red, blue, black, white, orange, green, gold
Gloss	high gloss
Application temperature	15-25°C
Dust free	10-15 min
Touch free	30-40 min
Hardened	after 24 h
Cover capacity	1,5-2 m ² depending on colour and type of surface by one application
High temperature resistance	up to 150°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	good
Alcohol resistance	moderate
Primer usage	recommended compatible DECO COLOR primers usage
Other coating applying	not recommended



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry. Primed surface should be grinded with fine-grained abrasive paper previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying). Drying time depends also on air humidity and product density. Painting should be made in well ventilated room. Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside. Perform the test spray. Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres. Wait few minutes between each layer when applying. When finished, clean the nozzle. Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 04 from 25/03/2014