



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name

CHROME EFFECT by DECO COLOR® aerosol line

Article No

400 ml : 12 240; 12 250; 12 260
150 ml : 12 270; 12 280

Seller/Manufacturer

Chemmot Ewa & Jerzy Kumorek spółka jawna; Piłsudskiego 59, 32-050 Skawina, Polska

Product's description

High quality acrylic lacquer with shiny metal chrome effect, achieved because of metallic dust „leafing extra”. Recommended for smooth surfaces made of metal, wood, aluminium, glass, ceramics, stone, concrete and some plastics.
Especially practical for works of art and decoration. At florists can be used for fresh and artificial flowers. Chrome effect line has one of the best reputations among competitive products on the market.

Main features

High gloss – mirror effect
Very good covering
Limited abrasion resistance – covering with additional clear coat impossible due to technological reasons
For indoor and outdoor use
CFC free
Do not use any primers previously

Physical and Chemical Properties

Capacity	150/400 ml
Base/resin	acrylic modified resin
Colour	gold, silver and cooper
Gloss	high gloss – mirror effect
Application temperature	15-25°C
Dust free	5-10 min
Touch free	20-30 min
Hardened	18-24 h
Cover capacity	400ml=1,5-2 m ² ; 150ml=0,8 m ² depending on colour and type of surface by one application
High temperature resistance	up to 150°C
VOC content	about 86%
Solids content	about 14%
Petrol resistance	insufficient
Alcohol resistance	good
Primer usage	not recommended
Other coating applying	impossible



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.
Notice: Do not use additional clear coat protection. Do not use any primers previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying). Drying time depends also on air humidity and product density.
Painting should be made in well ventilated room.
Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.
Perform the test spray.
Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.
Wait few minutes between each layer when applying.
When finished, clean the nozzle.
Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 04 from 25/03/2014