



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name

RENOVATOR AGD by DECO COLOR® aerosol line

Article No

30 460

Seller/Manufacturer

Chemmot Ewa & Jerzy Kumorek spółka jawna; Piłsudskiego 59, 32-050 Skawina, Polska

Product's description

Fast drying acrylic lacquer for painting and renovation of: fridges, washing machines and other household appliances. Doesn't become yellow, has good thermal conductivity. Perfect for renovation of outside metal layers of household appliances. Provides smooth, durable surface, you can easily clean.

Main features

Heat resistance up to 100°C
Directly to household appliances
Resistant to moisture and rust
Creates smooth, glossy surface
Most popular colour: RAL 9016
Fast drying time: 5 minutes!
Very good coverage of the painted surface
Anticorrosive properties
Hard acrylic film resistant to water and abrasion
For indoor and outdoor use
Capacity 400 ml

Physical and Chemical Properties

Capacity	400 ml
Base/resin	acrylic modified resin
Colour	RAL 9016
Gloss	high gloss
Application temperature	15-25°C
Dust free	5 min
Touch free	15-20 min
Hardened	16-20 h
Cover capacity	1,5-2 m ² by one application
High temperature resistance	up to 100°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	good
Alcohol resistance	insufficient
Primer usage	recommended compatible DECO COLOR primers usage
Other coating applying	possible



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry. Primed surface should be grinded with fine-grained abrasive paper previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying). Drying time depends also on air humidity and product density. Painting should be made in well ventilated room. Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside. Perform the test spray. Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres. Wait few minutes between each layer when applying. When finished, clean the nozzle. Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 04 from 25/03/2014