



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name	
ZINC PRIMER by DECO COLOR® aerosol line	
Article No	
30 690	
Seller/Manufacturer	
Chemmot Ewa Kumorek spółka komandytowa; Józefa Piłsudskiego 59, 32-050 Skawina, Polska	
Product's description	
Preparation with high content of zinc (97%). Designed to protect the surface made of metal and steel. Perfect for small craft works such as welding. In industry: rust protection of all structures. Perfect primer for installations exposed to water and hard weather conditions.	
Main features	
Creates hard coating which contains 97% of pure zinc Anticorrosive properties Weather condition and UV resistance Resistance to high temperatures up to 300°C Very good filling properties Spot welding ability For indoor and outdoor use CFC free	
Physical and Chemical Properties	
Capacity	400 ml
Base/resin	coumarin resin
Gloss	mat
Application temperature	15-25°C
Dust free	10-15 min
Touch free	30-40 min
Hardened	after 24 h
Cover capacity	1,0-1,5 m ² by one application
High temperature resistance	up to 300°C
VOC content	about 67%
Solids content	about 33%
Petrol resistance	insufficient
Alcohol resistance	good
Primer usage	n/a
Other coating applying	possible



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.
Compatible with all paint systems (alkyd, acrylic, nitro-combination) water and solvent based as well.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).
Drying time depends also on air humidity and product density.

Painting should be made in well ventilated room.

Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.

Perform the test spray.

Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.

Wait few minutes between each layer when applying.

When finished, clean the nozzle.

Put the container upside down, pressing the nozzle for the period of three seconds.

If it is necessary to paint the surface it is important to wait until zinc layer is dry then apply primer previously, than lacquer.

Technical Data Sheet version 05 from 01/03/2022